

KYDEX[®] L Laminating grade fire-rated sheet

Introduction

KYDEX[®] L thermoplastic sheet is very durable, damage resistant surfacing material that has been successfully used in many laminating applications including store fixtures, exhibits, dorrs and partitions.

General Information

Unilke most high-pressure laminates, colors is integral throughout teh sheet. It has excellent durability for easier handling. It is Class I/A rated for 1.0mm (0.040") and thinner and is listed by Underwriter's Laboratories, Inc[®] as UL Std 94 V-0. Notched Izod impact resistance is 801 J/m (15 ft/lbs/in).

Suggested Applications

- * Exhibits & Display
- * Store Fixture Components
- * Kiosk Housings

Features

- * tough and durable
- * solid, intergral color
- * chemical resistance
- * fire retardancy
- * resistance to cracking and chipping
- * very low moisture absorption
- * flexibility to allow small radius bends
- * thicknesses up to 8.13mm (0.318"), available in roll stock (< 1.0mm (0.040"))
- * expands and contracts with temperature fluctuations
- * can be thermoformed to produce 3-D parts with excellent detail
- * can be drill, punched, brake-formed or routed using standard metal and woodworking equipment
- * endorsed by the Royal Institute of Public Health for conformance to the standard of Hygenic Merit

Environmental and Safety Considerations

Kleerdex is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health and environmental protection. We support the safe handling of our products. Please contact our Technical Service department at 800.682.8758 for resources or visit our website: www.kydex.com. For Material Safety Data Sheets, please call 800.325.3133.

Kleerdex Company, LLC

ISO 9001 and ISO 14001 Certified


Customer Service

6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Outside the US: +1.570.389.5814
Fax: 800.452.0155, +1.570.387.7786
Email: info@kleerdex.com


Technical Service

Phone: 800.682.8758 ext. 581
Fax: +1.570.387.8722
Outside the US: +1.570.387.6997 ext.581

www.kydex.com



Durability by Design[®]



KYDEX® L Laminating grade fire-rated sheet

Physical Properties

Property	Test Method	Typical Value ¹	
Specific Gravity	ASTM D-792	1.35	
Tensile Strength	ASTM D-638	42 MPa	6,100 psi
Elongation %	ASTM D-638	110	
Flexural Strength	ASTM D-790	66 MPa	9,600 psi
Modulus of Elasticity	ASTM D-790	2,482 MPa	360,000 psi
Water Absorption %	ASTM D-570	0.07	
Notched Izod Impact Resistance @ 23°C (73°F)	ASTM D-256	801 J/m	15 ft-lbs/in
Coefficient of Linear Thermal Expansion	ASTM D-696	2.1 x 10 ⁻⁵ / °C	3.8 x 10 ⁻⁵ / °F
Rockwell Hardness (R Scale)	ASTM D-785	94	
Heat Deflection Temperature (HDT) @ 1.8 MPa (264 psi) annealed	ASTM D-648	75.5°C (annealed) 66.2°C (unannealed)	168°F (annealed) 151°F (unannealed)
Flammability: Underwriter's Laboratories, Inc® Component Recognition	UL Standard 94 ²	V-0 ³	
Surface Burning Characteristics: Flame Spread Smoke Developed	ASTM E-84 @ 1.02mm (0.040")	15 170	

¹ Values based upon 3.18mm (0.125") sheet unless otherwise specified.

² Underwriter's Laboratories, Inc®, File E115252

³ All thicknesses 0.71mm (0.028") and above

Not intended for specification purposes.

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use or our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our products. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.

Kleerdex Company, LLC

ISO 9001 and ISO 14001 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA

Phone: 800.325.3133, +1.570.389.5810

Outside the US: +1.570.389.5814

Fax: 800.452.0155, +1.570.387.7786

Email: info@kleerdex.com

Technical Service

Phone: 800.682.8758 ext. 581

Fax: +1.570.387.8722

Outside the US: +1.570.387.6997 ext.581